



HAL
open science

Identification of an optimized protocol for extraction and characterization of microplastics in seafood products

Ludovic Hermabessiere, Alexandre Dehaut, Anne-Laure Cassone, Laura Frère, Charlotte Himber, Emmanuel Rinnert, Gilles Rivière, Christophe Lambert, Philippe Soudant, Arnaud Huvet, et al.

► To cite this version:

Ludovic Hermabessiere, Alexandre Dehaut, Anne-Laure Cassone, Laura Frère, Charlotte Himber, et al.. Identification of an optimized protocol for extraction and characterization of microplastics in seafood products. Journées des Doctorants et Post-Doctorants de l'ANSES, Oct 2016, Maisons-Alfort, France. anses-03889580

HAL Id: anses-03889580

<https://anses.hal.science/anses-03889580>

Submitted on 8 Dec 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Identification of an optimized protocol for extraction and characterization of microplastics in seafood products

Ludovic Hermabessiere^a, Alexandre Dehaut^a, Anne-Laure Cassone^b, Laura Frère^b, Charlotte Himber^a, Emmanuel Rinnert^c, Gilles Rivière^d, Christophe Lambert^b, Philippe Soudant^b, Arnaud Huvet^e, Guillaume Duflos^a & Ika Paul-Pont^b

^a ANSES – Laboratoire de Sécurité des Aliments, Boulevard du Bassin Napoléon, 62200 Boulogne-sur-Mer, France; ^b Laboratoire des Sciences de l'Environnement Marin (LEMAR) – UMR6539 / UBO / CNRS / IRD / IFREMER – Institut Universitaire Européen de la Mer, Technopôle Brest-Iroise, Rue Dumont d'Urville, 29280 Plouzané, France; ^c IFREMER – Laboratoire Détection, Capteurs et Mesures (LDCM) – Centre Bretagne, ZI de la Pointe du Diable – CS 10070, 29280 Plouzané, France; ^d ANSES – Direction d'Évaluation des Risques, 14 rue Pierre et Marie Curie, 94701 Maisons-Alfort Cedex, France; ^e IFREMER – Laboratoire des Sciences de l'Environnement Marin (LEMAR) – UMR 6539 / UBO / CNRS / IRD / IFREMER, 29280 Plouzané, France



Email: ludovic.hermabessiere@anses.fr


Ifremer

Introduction

Microplastics particles (<5 mm) are found in the Oceans worldwide and ingestion by marine species have been recently described. Microplastics can also represent a threat for human consumers through the consumption of seafood products. To date, a few studies have investigated the levels of contamination collected *in situ*. It is crucial for microplastics extraction to use solvent(s) or chemical(s) allowing efficient tissue dissolution without degrading plastic polymers. The purpose of this work was to benchmark six existing protocols on fifteen plastics polymers and assess their impact on polymers integrity coupled with an efficient digestion of biological matrices.


Material and methods

Experiment 1 : Testing 6 different protocols on plastics integrity



Fifteen tested families : high and low density polyethylene (HDPE & LDPE), polypropylene, (PP) expanded polystyrene (ePS), crosslinked polystyrene (PSXL), polystyrene (PS), poly(methyl-methacrylate) (PMMA), poly(laurylactam) (PA-12), polycaprolactam (PA-6), polyethylene terephthalate (PET), polyurethane (PUR), polytetrafluoroethylene (PTFE), unplasticized polyvinyl chloride (uPVC), polycarbonate (PC) and cellulose acetate (CA)

Experiment 2 : Application of selected protocols on seafood products



Results and discussion

Experiment 1




Figure 1 : Pictures of plastics degraded using protocol 3, protocol 4 and protocol 5. White bars represents 1mm

During experiment 1, with protocol 3 and 4, PA-12 plastic are partially degraded and with protocol 5 PC is totally degraded (Figure 1). Moreover, protocol 2 using pepsin is too expensive to be kept to be applied in field survey. Finally none of these protocols (2, 3, 4 and 5) were kept as promising protocols for the following experiment 2. Protocols 1 and 6 were used for experience 2 as they have no impact on plastic integrity and identification using Pyrolysis-GC/MS and Raman spectrometry.

Conclusion

Protocol 1 using KOH 10% at 60°C during 24h at 300rpm is proposed to be a suitable protocol for extraction and characterization of microplastics in seafood products. This protocol should be recommended by international bodies. The selected protocol is now apply in a field study to determine the prevalence of microplastics in the major seafood products consumed in France.

Experiment 2




Figure 2 : Comparison of digestion efficiency for three musells treated with protocol 1 (M1 to M3) and with protocol 6 (M4 to M6)




Figure 3 : Musells filters after digestion with protocol 1 (a) and protocol 6 (b)

During experiment 2, protocol 6 did not efficiently digest whole musells (Figure 2) as pieces of musells were still visible (Figure 3b). Protocol 1 allowed a good filtration and revealed negligible debris (Figure 3a) on the filter after digestion of musells. Digestion of velvet crabs and black seabreams using protocol 1 led to easy filtration and observable filters.

Acknowledgments

Ludovic Hermabessiere is thankful to Région Hauts de France—Nord Pas de Calais Picardie and Anses for the financial support of his PhD grant.

